

ABSTRACT OF THE DISCLOSURE

he invention relates to a melted and cast refractory product which is intended, for example, for a checker work element of a glass furnace regenerator, having the following average chemical weight composition, expressed in weight percent based on oxide content: $0.4 \% < \text{MgO} < 2.5 \%$; $0.2 \% < \text{SiO}_2 < 2 \%$; $\text{CaO} < 0.4 \%$; impurities $< 0.5 \%$ Al_2O_3 : complement.